



J.R. Paine & Associates Ltd.

CONSULTING AND TESTING ENGINEERS
EDMONTON - GRANDE PRAIRIE - PEACE RIVER

SCREEN ANALYSIS

Sample: SA 608 Depth: _____
Location: TerraPro

Client: TerraPro Inc.
Project: General Testing - Hub Inventory Crushing
Made By: JMH File: Edmonton General
Ck'd By: [Signature] Date: July 13, 2022


Sieve No.	Size of Opening millimetres	Specifications		Percent Finer Than	Percent Finer Than Basis Original Sample
		Minimum	Maximum		
50,000	50.0				
40,000	40.0				
25,000	25.0				
20,000	20.0				
12,500	12.5				
10,000	10.0	100	100		100.0
5,000	5.0	70	100		71.1
2,500	2.5				47.9
2,000	2.0				42.8
1,250	1.25				34.9
630	0.630				27.1
400	0.400				21.2
315	0.315				17.9
160	0.160	5	20		11.2
80	0.080	0	12		7.1

Description of Sample: _____
City of Edmonton 7-10 Bedding Sand

Method of Preparation: Dry Washed
Moisture Content: 4.1 % 2 Face Crush Count = _____ %

3000
Time of Sieving: 15 minutes

Remarks: _____
Sampled & Delivered By Client.
Attention: Otis Closson oclosson@terraproinc.com





J.R. Paine & Associates Ltd.

CONSULTING AND TESTING ENGINEERS
EDMONTON - GRANDE PRAIRIE - PEACE RIVER

SCREEN ANALYSIS

Sample: SA 609 Depth: _____
Location: TerraPro

Client: TerraPro Inc.
Project: General Testing - Hub Inventory Crushing
Made By: JMH File: Edmonton General
Ck'd By: K. [Signature] Date: July 13, 2022


Sieve No.	Size of Opening millimetres	Specifications		Percent Finer Than	Percent Finer Than Basis Original Sample
		Minimum	Maximum		
50,000	50.0				
40,000	40.0				
25,000	25.0				
20,000	20.0				
12,500	12.5				
10,000	10.0	100	100		100.0
5,000	5.0	70	100		67.4
2,500	2.5				45.4
2,000	2.0				41.2
1,250	1.25				34.4
630	0.630				26.3
400	0.400				20.6
315	0.315				17.4
160	0.160	5	20		11.2
80	0.080	0	12		7.1

Description of Sample: _____
City of Edmonton 7-10 Bedding Sand

Method of Preparation: Dry Washed
Moisture Content: 5.1 % 2 Face Crush Count = _____ %

4000
Time of Sieving: 15 minutes

Remarks: _____
Sampled & Delivered By Client.
Attention: Otis Closson oclosson@terraproinc.com





J.R. Paine & Associates Ltd.

CONSULTING AND TESTING ENGINEERS
EDMONTON - GRANDE PRAIRIE - PEACE RIVER

SCREEN ANALYSIS

Sample: SA 610 Depth: _____
Location: TerraPro

Client: TerraPro Inc.
Project: General Testing - Hub Inventory Crushing
Made By: JMH File: Edmonton General
Ck'd By: K. [Signature] Date: July 13, 2022

Sieve No.	Size of Opening millimetres	Specifications		Percent Finer Than	Percent Finer Than Basis Original Sample
		Minimum	Maximum		
50,000	50.0				
40,000	40.0				
25,000	25.0				
20,000	20.0				
12,500	12.5				
10,000	10.0	100	100		100.0
5,000	5.0	70	100		65.0
2,500	2.5				44.7
2,000	2.0				40.9
1,250	1.25				34.3
630	0.630				26.9
400	0.400				21.1
315	0.315				18.0
160	0.160	5	20		12.0
80	0.080	0	12		8.3

Description of Sample: _____
City of Edmonton 7-10 Bedding Sand

Method of Preparation: Dry Washed
Moisture Content: 4.3 % 2 Face Crush Count = _____ %

5000
Time of Sieving: 15 minutes

Remarks: _____
Sampled & Delivered By Client.
Attention: Otis Closson oclosson@terraproinc.com

